



INTERNATIONAL GEMOLOGICAL INSTITUTE

SCIENTIFIC LABORATORY FOR THE IDENTIFICATION AND GRADING
OF DIAMOND AND COLORED STONES

EDUCATIONAL PROGRAMS

Expertise issued by IGI (HK) Ltd.

Suite 501, Tower 1, The Gateway, Harbour City,
25 Canton Road, Tsim Sha Tsui - Hong Kong
Tel. +852 2522 9880 - Fax +852 2522 9887
E-mail : hk@igiworldwide.com
www.igiworldwide.com

DIAMOND REPORT

This report is a statement of the diamond's identity
and grade including all relevant information.

NUMBER M3B86450

HONG KONG, December 22, 2016

LABORATORY REPORT (ORIGINAL)


TO WHOM IT MAY CONCERN.

DESCRIPTION
SHAPE AND CUT
WEIGHT
MEASUREMENTS
CLARITY GRADE
COLOR GRADE
FLUORESCENCE
TREATMENT
FINISH AND SYMMETRY
PROPORTIONS
TOTAL DEPTH
TABLE DIAMETER
CROWN HEIGHT
PAVILION DEPTH
GIRDLE THICKNESS
CULET SIZE
COMMENTS

NATURAL DIAMOND
PRINCESS CUT
1.34 Carat
5.65 x 5.43 x 4.92 mm
INTERNALLY FLAWLESS
H
VERY SLIGHT
VERY GOOD
GOOD
91.1%
72.5%
22.5%
65%
THIN TO SLIGHTLY THICK
POINTED

Laserscribe on Girdle:
IGI M3B86450

The symbols do not usually reflect the size of the characteristics.
Red symbols indicate internal characteristics.
Green symbols indicate external characteristics.



Insignificant external details, visible under
high magnification only, are not shown



0-m Security features included in this document are hologram,
watermarked paper and additional features not listed,
that, as a composite, exceed industry security standards.



CLARITY GRADE: Internally Flawless VVS₁ VVS₂ VS₁ VS₂ SI₁ SI₂ I₁-P₁ I₂-P₂ I₃-P₃

COLOR GRADE: D E F G H I J K L M N O P Q R S-Z FANCY COLOR

PROPORTION - MARGIN: ± 1%
MEASUREMENTS - MARGIN: ± 0.02mm

The gemological analysis of diamonds, precious stones and other minerals must be carried out by gemologists with many years experience in this field who have a keen sense of the professional code of ethics governing their work as well as a thorough knowledge of crystallographic, optical and physical phenomenon.

The identification of the various species and varieties of stones, the distinction between natural and synthetic material, as well as various treatment methods currently encountered are all very sensitive factors. More specifically for diamonds, the laws of refraction and dispersion of light, the related geometric data as well as knowledge of all aspects involved in the cutting process are essential.

This gemological report is provided upon request of the customer and/or the owner of the gem. By making this report IGI does not agree to purchase or replace the article. Neither IGI nor any member of its staff shall, at any time, be held responsible for any discrepancy which may result from the application of other grading methods. Neither the client nor any purchaser of the gem shall regard this Report as an appraisal nor as a guaranty or warranty.

This report is subject to the terms and conditions set forth above and on reverse.

© IGI, 2000, edition 2013

All rights reserved. No part of this report may be reproduced or transmitted in any form or by any means, without permission in writing from International Gemological Institute